


# Certificate of Analysis

Polymer type: Poly(vinyl pyrrolidone) broad  
 Part No: PSS-vpr70k  
 Lot No: vpr66k

## Molar Mass Distribution



## GPC/SEC - Conditions

Sample concentration	3.00 g/l	Injection volume	20 µl
Solvent	0.1M NaNO <sub>3</sub> , 20%CH <sub>3</sub> CN	Flow rate	1.0 ml/min
Data Acquisition Software	PSS WinGPC		

## GPC/SEC - Results

Detector	Mw [Da]	Mn [Da]	Mp [Da]	PDI [Mw/Mn]
Shodex 71	65900	8000	-	8.24


**Note:**

- Mw = Weight average molecular weight
- Mn = Number average molecular weight
- Mp = Molar mass at the peak maximum
- PDI = Polydispersity Index

**Storage:** Store the tightly recapped polymer standard in a dry, dark, cool area; e.g. a refrigerator (4 °C).

**Date of expiry:** See product label.

Manufacture control according to PSS method of analysis



Dr. T. Hofe  
production director



**PSS Polymer Standards Service GmbH**  
 In der Dalheimer Wiese 5  
 55120 Mainz | Germany

**Phone** +49 6131 96239-0  
**Fax** +49 6131 96239-11  
**E-Mail** info@pss-polymer.com  
**Web** www.pss-polymer.com

**Polymer Standards Service-USA, Inc.**  
 160 Old Farm Rd, Suite A  
 Amherst | MA 01002 | USA

**Phone** +1 413 835-0265  
**Fax** +1 413 835-0354  
**E-Mail** usa@pss-polymer.com  
**Web** www.pss-polymer.com